



MORICHAL

# Morichal Kraftliner T

## Ortalama Değerler, Typical Values

Parametre Parameter	Birim Unit	Test Metodu Standard	70	100	110	135
<b>Gramaj</b> Grammage	gr/m <sup>2</sup>	ISO 536	70	100	110	135
<b>Nem</b> Moisture	%	ISO 287	7	7	7	7
<b>SCT</b>	kN/m	ISO 9895	1,15	1,7	1,8	2,2
<b>Patlama</b>	kPa	ISO 2759	165	210	225	265
<b>RCT</b>	kN/m	ISO 12192	0,45	0,85	1,1	1,4
<b>CoBB,60</b>	g/mn	ISO 535	50	50	50	50

## Garanti Edilen Değerler, Guaranteed Values

Parametre	Birim Unit	Test Metodu Standard	70	100	110	135
<b>Gramaj</b> Grammage	g/m <sup>2</sup>	ISO 536	+-%3	+-%3	+-%3	+-%3
<b>Nem</b>	%	ISO 287	+1,5	+1,5	+1,5	+1,5
<b>SCT,min</b>	kN/m	ISO 9895	0,9	1,5	1,6	1,7
<b>Patlama</b>	kPa	ISO 2759	135	180	190	200
<b>Bobin çapı</b> Bobbin Diameter	cm		140	140	140	140
<b>Mihver Çapı</b> Core Diameter	mm		100	100	100	100

Ölçüm koşulları: Bağıl nem – %50 ±2, Sıcaklık 23 ±1°C  
 Measuring conditions: Relative Humidity - %50 ±2, Temperature 23 ±1°C  
 Ocak 2017 itibarıyla geçerlidir. Valid starting from January 2017.